






KOBE STEEL's High Performance Copper Alloy Strips for Terminals and Connectors.

Click  links to see the detail.

Properties		Alloys	 KFC™	KLF™-2	 KLF™-5	 CAC™5	CAC™16	CAC™19	 CAC™60	 CAC™75	
		CDA No.	C19210	-	C50715	C19040	C19800	C19419	C64760	C64780	
Chemical Compositions		wt% (Nominal)	Cu Rem. Fe 0.1 P 0.03	Cu Rem. Fe 0.1 P 0.03 Sn 0.1	Cu Rem. Fe 0.1 P 0.03 Sn 2	Cu Rem. Ni 0.8 P 0.07 Sn 1.2	Cu Rem. Fe 0.1 P 0.03 Zn 0.4 Sn 0.2 Mg 0.2	Cu Rem. Fe 1.9 Si 0.05 Zn 0.15 Sn 0.1 Mg 0.1	Cu Rem. Ni 1.8 Si 0.4 Zn 1.1 Sn 0.1	Cu Rem. Ni 2.5 Si 0.55 Zn 1 Sn 0.2	
Physical Properties (Typical)	Specific Gravity		8.9	8.9	8.9	8.9	8.9	8.9	8.9	8.9	
	Coefficient of Thermal Expansion (293 ~ 573K)	×10 ⁻⁶ /K	17.5	17.5	17.6	17.7 (Temper SP)	17.6	17.9	17.3	17.6	
	Thermal Conductivity	W/m·K	364	318	150	166 (Temper SP)	247	254	197	166	
	Electrical Resistivity	nΩ·m	18.2	21.6	49.3	43.1 (Temper SP)	28.3	27.4	39.2	43.1	
	Electrical Conductivity	%IACS	90	80	35	40 (Temper SP)	61	63	44	40	
	Modulus Elasticity	GPa	125	127	123	130	118	120	127	127	
	Poisson's Ratio		0.33	0.33	0.33	0.33	0.33	0.33	0.33	0.33	
Mechanical Properties	Temper 1/4H	Tensile Strength	MPa	295~370	330 min	/	/	/	365~450	/	/
		Elongation	%	15 min	13 min				15 min		
		Vickers Hardness	MHv: 4.9N	85~110	80~120				90~140		
	Temper 1/2H	Tensile Strength	MPa	350~430	/	440~540	/	335~470	/	/	/
		Elongation	%	4 min		8 min		8 min			
		Vickers Hardness	MHv: 4.9N	100~130		140~180		100~150			
	Temper H (H/SP: CAC5)	Tensile Strength	MPa	390~470	390 min	530~640	500~590	450~550	470~580	600~700	700~850
		Elongation	%	2 min	7 min	5 min	7 min	5 min	5 min	10 min	5 min
		Vickers Hardness	MHv: 4.9N	120~145	120~160	160~200	155~185	130~170	140~175	180~220	210~260
	Temper EH (EH/SP: CAC5)	Tensile Strength	MPa	/	/	590 min	540~630	/	/	640~740	/
		Elongation	%			-	5 min			3 min	
		Vickers Hardness	MHv: 4.9N			180 min	165~200			190~230	